



Technical Data Sheet

RLD9006_MS

November 2020

International Master - for professional use only

Product List

DELFLEET ONE® RAL9006 Aluminium Ready Mix Topcoat	
Product	Description
F8050-9006	RAL9006 Aluminium Ready Mix
F7xxx	Coloured Toners
F8286	MS Hardener - Medium
F8284	MS Hardener - Slow
F8374	MS Thinner - Slow
F8375	MS Thinner - Medium
F8376	MS Thinner - Fast

Product Description

DELFLEET ONE® RAL9006 Aluminium Ready Mix is a 2-pack polyurethane topcoat formulated to get an optimal application of silver colours in a simple 2-coats single stage process.

It provides a good quality finish to Commercial Vehicles without any need to spray a clearcoat on top.

Delfleet One RAL9006 Aluminium Ready Mix is an easy to spray topcoat providing good opacity, gloss and general appearance which meets the standards demanded for Commercial Transportation Vehicles.


It can be combined with a flexible offer of ancillaries to meet the needs of both Builders and Repairers in different application conditions, this in a simple two wet coats application process.



DELFLEET
ONE®

Substrates and Preparation

PREPARE THE SUBSTRATE AS FOLLOWS:



Substrates:

- Original finishes and work in sound condition need to be degreased, cleaned and dry sanded with P320-P400 (or P600 wet) prior to topcoat application.
- Steel, Aluminum, GRP & Zinc coated steel need to be pre-primed with the appropriate primer in order to ensure correct intercoat adhesion and substrate protection.
- DELFLEET ONE® RAL9006 Aluminium Ready Mix is suitable over all PPG primers, surfacers and sealers.




Cleaning:

The substrate to be painted must be dry, clean, free of corrosion, grease & mould release agents.

Substrates need to be thoroughly prepared using a combination of D845 Degreaser & D837 Spirit Wipe (or D8401 low V.O.C cleaner).

Process

CONVENTIONAL or PRESSURE POT APPLICATION



Mixing Ratio by Volume:

DELFLEET ONE® RAL9006 Aluminium Ready Mix	2.5
F828X MS Slow / Medium Hardener	1
F837X MS Slow / Medium / Fast Thinner	1.2-1.5

Recommended combinations:


Temperature	<18°C	18-25°C	25-30°C	>30°C
Combination	Medium/Fast	Medium/Medium	Medium/Slow	Slow/Slow
Ancillaries	F8286/F8376	F8286/F8375	F8284/F8374	F8284/F8374



Potlife at 20°C: 3 Hours


Application Process

CONVENTIONAL or PRESSURE POT APPLICATION



Spray Viscosity at 20°C:

17-18 seconds DIN4




1.4-1.5 mm Gravity or suction feed at 2.0-2.4 bars

OR



0.8-1.0 mm Pressure Pot
Air Cap Pressure: 0.68 bar
Paint Pressure: 0.3-1.0 bar
Fluid flow rate: 280-320 cc/min




Number of Coats

2 coats:
1 Full coat
+ 1 Full coat


Dry Film Thickness:

40 – 60 µm



Flash-Off between coats:
Flash-Off before bake:

2 coats:
10-15 minutes
15-20 minutes



Drying Time:

20°C Dust free:
20°C Through dry
60°C Bake (metal temp.)

10-20 min
24 hours
30 min

IR Medium Wave

10-15 min.



Colour

COLOUR MIXING and TINTING

All Toners should be thoroughly hand stirred when first opened, and then stirred on a mixing machine for 10 minutes before use. Thereafter all Toners should be machine stirred twice a day for at least 10 minutes.

F8050-9006 can be tinted with up to 10% F7xxx DELFLEET ONE® Toners

COLOUR CHECKING

As with all refinish paint systems, a colour check should be carried out before painting the vehicle.

General Process Notes

DECAL APPLICATION

It is recommended that DELFLEET ONE® F8050-9006 Topcoat is allowed to cure for at least one week prior to any decal application.

COVERAGE

Approximately 6 to 8m² per litre of ready for use paint at a dry film thickness of 50 microns depending on thinning ratio used.

OTHER POINTS TO NOTE

Allow finishes to harden thoroughly before subjecting to vehicle washes. This can take a number of weeks if vehicles are air-dried in cold conditions and/or paint film thickness is excessively high.

STORAGE

Mixing Room Temperature:

Store F7xxx Toners and F8050-9006 in the Mixing Room between the following temperatures: 18 to 25°C.

Storage Temperature:

Store F7xxx Toners and F8050-9006 between the following temperatures: 5 to 35°C (41 to 95°F).

Store in accordance with local regulations. Store in original container protected from direct sunlight in a dry, cool and well-ventilated area, away from incompatible materials and food and drink. Keep container tightly closed and sealed until ready for use.

Containers that have been opened must be carefully resealed and kept upright to prevent leakage.

Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination. Always refer to the Material Safety Data Sheet.



DELFLEET
ONE®



HEALTH AND SAFETY

These products are for professional use only, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose. For Health and Safety information please refer to the material Safety Data Sheet, also available at: www.ppgrefinish.com

For further information please contact:

Customer Service Sales Group

PPG Industries (UK) Ltd

Needham Road

Stowmarket

Suffolk IP14 2AD

Tel: 01449 771771

Fax: 01449 773472

The PPG Logo, Delfleet, Delfleet One and PaintManager are registered trademarks and RapidMatch is a trademark of PPG Industries Ohio, Inc.
© 2019 PPG Industries, all rights reserved. Copyright in the above product numbers that are original is asserted by PPG Industries.

THESE PRODUCTS ARE FOR PROFESSIONAL USE ONLY.

